

**Zinkoxyd aktiv<sup>®</sup>****Product Description**

fine particles of precipitated zinc oxide

**Supply Form**

white to slightly yellowish powder

**Product Characteristics**

<b>Property</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Content of zinc oxide	≥ 93.0	%	169
Ignition loss	≤ 4.0	%	178
Sieve residue (0.063)	≤ 0.2	%	DIN ISO 787/18

**Zinkoxyd aktiv<sup>®</sup>****Other Product Features**

<b>Property</b>	<b>Typical Value</b>
Density	5.0 g/cm <sup>3</sup>
Specific surface area	45 m <sup>2</sup> /g
Volatile matter (at 110 °C)	0.4 %
Lead content	3 ppm
Cadmium content	2 ppm
Packaging	20 kg paper bags on pallets
Storage Life/Conditions	18 months from date of production, keep cool (approximately 25 °C) and dry in closed original packaging
Product Safety	Relevant safety data and references as well as any necessary warning labels are to be found in the EU safety data sheet MSDS-Number: 00010227

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

Zinkoxyd aktiv<sup>®</sup> is a Registered Trademark of LANXESS Deutschland GmbH

Issue number: 10 / Date of issue: September 07, 2006 / Previous issue from June 14, 2006

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.